

Report No.: TMC200320111-S



Test Report

On Behalf of

Youshi protective equipment (Hangzhou) Co., Ltd

FFP2 MASK

Model: 3000, 1015, 2007, 3000V, 3011, 3100, 5011, 5012, 5013, 5014

Prepared for: Youshi protective equipment (Hangzhou) Co., Ltd

NO.296 NanYang Road Cheng Nan Gong Ye District Mei

Cheng Town Jian De City, HangZhou, Zhejiang

Prepared By: TMC Testing Services (Shenzhen) Co., Ltd.

1st Floor, Block A1, Zone A, Xinshidai Gongrong Industrial Park, No. 2, Shihuan Road, Shiyan Street, Baoan District,

Shenzhen, China

Tel: +86-755- 86642861 Web: www.tmc-lab.com E-mail: Cert@tmc-lab.com



TEST REPORT

EN 149

Respiratory protective devices. Filtering half masks to protect against particles. Requirements, testing, marking

Report Reference No...... TMC200320111-S

Checked by

(printed name and signature) ...:

Seven Lin

Report No.: TMC200320111-S

Approved by

(printed name and signature) ...

Lemon Rao

Seven Liu

Date of issue...... March 23, 2020

Testing laboratory.....: TMC Testing Services(Shenzhen) Co., Ltd.

Address......: 1st Floor, Block A1, Zone A, Xinshidai Gongrong Industrial Park,

No. 2, Shihuan Road, Shiyan Street, Baoan District, Shenzhen,

China

Applicant's name : Youshi protective equipment (Hangzhou) Co., Ltd

Address...... NO.296 NanYang Road Cheng Nan Gong Ye District Mei Cheng

Town Jian De City, HangZhou, Zhejiang

Manufacturer's name......: Youshi protective equipment (Hangzhou) Co., Ltd

Address.....: NO.296 NanYang Road Cheng Nan Gong Ye District Mei Cheng

Town Jian De City, HangZhou, Zhejiang

Factory's name..... Same as applicant

Address....::

Test specification:

Test procedure : CE
Non-standard test method : N/A

Test Report Form No.....: TMC200320111-S

TRF Originator.....: TMC

Master TRF.....: Dated 2019-01

Test item description.....: FFP2 MASK

Trade Mark..... GYWS

Ratings.....: --



Report No.: TMC200320111-S

Possible test case verdicts:

- test case does not apply to the test object ... N (Not apply)
- test object does meet the requirement......P (Pass)
- test object does not meet the requirement..... F (Fail)

Testing

Date of receipt of test item March 13, 2020

Date(s) of performance of tests March 13, 2020 to March 23, 2020

General remarks:

The test results presented in this report relate only to the object tested.

This report shall not be reproduced, except in full, without the written approval of the Issuing testing laboratory.

"(See Enclosure #)" refers to additional information appended to the report.

"(See appended table)" refers to a table appended to the report.

General product information:

N/A

Copy of marking plate:

FFP2 MASK

Model:3000

Standard: EN 149:2001+A1:2009

Classification: FFP2



Youshi protective equipment (Hangzhou) Co., Ltd

Made in China



Report No.: TMC200320111-S EN 149 Result - Remark Clause Requirement - Test Verdict

	4 7 7 7 7		4 7 7 7 7		4 7 7 7 7	4 5 5 5 7	
5	Classification	11,	11-	110	11	110	
nin C	Particle filtering hat their filtering efficience leakage. There are	ency and th	neir maximum		NIC	· wnC	Р
11.	- FFP1	11.	1.	11.	11.	11.	N
	- FFP2				>95%		Р
21/2	- FFP3	NINC.	ay C	an C	a'NC	ain C.	N

6	Designation		
THE	Particle filtering half masks meeting the requirements of this European Standard. Year of publication, classification, option	Particle filtering half mask EN149:2001+A1:2009 FFP2 NR.	Р

711	Requirements	· anc anc	
7.1	General	14. 14.	Р
	All test all test samples shall meet the requirements.	Compled the requirement, see bellow	Р
7.2	Nominal values and tolerances	Mr. Mr.	Р
1,,	Unless otherwise specified,the values stated in this European Standard are experature limits.	7, 7,	Р
7.3	Visual inspection		Р
14/1	The visual inspection shall also include the marking and the information supplied by the manufacturer.	Clear marking is provided, see sample body	P
7.4	Packaging	9	Р
TANC	Particle filtering half masks shall be offered for sale packaged in such a way that they are protected against mechanical damage and contamination before use.	LING LING	PI
7.5	Material		Р
L MILC	Materials used shall be suitable to withstand handling and wear over the period for which the particle filtering half mask is designed to be used. Any material from the filter media released by the air flow through the filter shall not constitute a hazard or nuisance for the wearer.	Comfortable wearing, when releasing no hazards is produced.	Р
7.6	Cleaning and disinfecting	- in - in	N
MC	If the particle filtering half mask is designed to be re- usable, the materials used shall withstand the cleaning and disinfecting agents and procedures to be specified by the manufacturer.	It's is not re-usable.	N
7.7	Practical performance	10 10	P
. (The particle filtering half mask shall undergo practical performance tests under realistic conditions.	Complied, see append test.	Р
7.8	Finish of parts	LAL LAL	Р
	come into contact with the wearer shall have no sharp edges or burrs		Р
7.9	Leakage	See append table 8.5	Р
7.9.1	Total inward leakage	₹₽. ₹₽.	Р



Access to global market
TMC Testing Services(Shenzhen) Co., Ltd Report No.: TMC200320111-S

	EN 149	1.	
Clause	Requirement – Test	Result - Remark	Verdic
a (8
1 1911	The laboratory tests shall wearer to protect with high probability against the potential hazard to be expected.	Enough safe condition is Provide.	P
- (Exercise results for total inward leakage shall be not greater than		Р
THIN	25% for FFP1 11% for FFP2 5% for FFP3	FFP2, Not exceed 11%	Р
THIC	And, in addition, at least 8 out of the 10 individual wearer arithmetic means for the total inward leakage shall be not greater than.	THIC THIC	Р
	22 % for FFP1 8 % for FFP2 2 % for FFP3.	FFP2, Not exceed 8%	Р
7.9.2	Penetration of filter material	1 p. 1 p.	P
	The penetration of the filter of the particle filtering half mask shall meet the requirements of Table 1.	see append table 7.92	Р
7.10	Compatibility with shin	anc anc	Р
110	Materials that may come into contact with the wearer's skin shall not be known to be likely to cause irritation or any other adverse effect to health.	Lu. Lu.	Р
7.11	Flammability	and and	Р
110	The material used shall not present a danger for the wearer and shall not be of highly flammable nature.	Ap. Ap.	Р
7.12	Carbon dioxide content of the inhalation air	((Р
11/1	The carbon dioxide content of the inhalation air (dead space) shall not exceed an average of 1,0% (by volume).	<1.0%	P
7.13	Head harness		Р
THIC	Head harness shall be designed can be donned and removed easily and adjustable or selfadjusting and sufficiently robust to hold the particle.	Head harness is donned and removed easily	P
7.14	Field of vision		Р
·WC	Field of vision is acceptable in practical performance tests.	Clear field of vsion when wearing	Р
7.15	Exhalation valve(s)	7	N
NAC	A particle filtering half mask may have one or more exhalation valve(s) and shall function correctly in all orientations.	One valve provided	N
\\ (Exhalation valve is provided it shall be protected against or be resistant to dirt and mechanical damage and may be shrouded or may include any other device.	Clearly function	N
1 kills	Exhalation valve(s) shall continue to operate correctly after a continuous exhalation flow of 300 l/min over a period of 30 s.	Line Line	N
an C	Exhalation valve housing is attached to the faceblank, and withstand axially a tensile force of 10 N applied for 10 s.	anc anc	N
7.16	Breathing resistance	1/10. 1/10.	P
	Ereathing resistances apply to valved and valveless and shall meet the requirements.		Р
7.17	Clogging	Who will	N
11.	General	1, 1,	N



./ .	EN 149	1. 1.	
Clause	Requirement – Test	Result - Remark	Verdict
- W	For single-use devices clogging test is an optional test.	The The	N 💉
11.	Devices designed to be resistant to clogging, shown by a	41, 41,	
	slow increase		N
- WC	The specified breathing resistances shall not be exceeded before the required dust load of 833 mg·h/m³.	WC WC	N
7.17.2	Breathing resistance	7, 7,	N
7.17.2.1	Valved particle filtering half masks	7 1	N
7.17.2.2	Valveless particle filtering half masks	- Me - Me	N
7.17.3	Penetration of filter materia	7, 7,	N
THIC	All types claimed to meet the clogging requirement shall also meet the penetration requirements given in 7.9.2 after the treatment.	THIC THIC	N
7.18	Demountable parts		N
	All demountable parts (if fitted) shall be readily connected and secured, where possible by hand.	No such demountable part	N
1/1/2	Les Les Les Les	1 kg, 1 kg,	<
8	Testing		
8.1	General	nC .nC	Р
1411	No special measuring devices and methods are specified, commonly used devices and methods shall be used.	Lun Lun	Р
8.2	Visual inspection	, ,	Р
~ W	The visual inspection is carried out appropriate by the test house prior to laboratory or practical performance tests.	Line Line	P
8.3	Conditioning	,	Р
8.3.1	Simulated wearing treatment	.(.(Р
164	A breathing machine is adjusted to 25 cycles/min and 2,0 l/stroke.	25 cycles/min 2,0 l/stroke.	P
N/A	For testing, a saturator is incorporated in the exhalation line between the breathing machine and the dummy head,	A saturator incorporated by breathing machine and the dummy head.	Р
11.	The spilling out of the dummy's mouth and contaminating the particle filtering half mask the head shall be incline	Incline considered	Р
8.3.2	Temperature conditioning	. (. (Р
1 Billion	Exposet masks to the following thermal cycle:	The This	P
	a) for 24 h to a dry atmosphere of (70 ± 3) °C;		Р
	b) for 24 h to a temperature of (-30 ± 3) ℃;		Р
LINE	Allow to return to room temperature for at least 4 h between exposures and prior to subsequent testing.	5h to paid for	P
8.3.4	Flow conditioning		Р
THIC	A total of 3 valved particle filtering half masks shall be tested, one as received and two temperature conditioned in accordance with 8.3.2.	IMC IMC	Р
9	Marking	one one	
9.1	Packaging	160, 160	P



Access to global market
TMC Testing Services(Shenzhen) Co., Ltd Report No.: TMC200320111-S

11/2	EN 149	1. Lu.	<
Clause	Requirement – Test	Result - Remark	Verdict
1 km	The following information shall be clearly and durably marked on the smallest commercially available packaging or legible through it if the packaging is transparent.	Complied, clearly marked	Р
9.1.1	The name, trademark or other means of identification of the manufacturer or supplier.	anc anc	Р
9.1.2	Type-identifying marking.	1/2 1/2	Р
9.1.3	Classification: FFP1, FFP2, FFP3.	FFP2 NR	Р
9.1.4	The number and year of publication of this European Standard.	THE THE	Р
9.1.5	At least the year of end of shelf life.		Р
9.1.6	The sentence 'see information supplied by the manufacturer', at least in the official language(s) of the country of destination, or by using the pictogram as shown in Figure 12b.	THIC THIC	Р
9.1.7	The manufacturer's recommended conditions of storage (at least the temperature and humidity) or equivalent pictogram, as shown in Figures 12c and 12d.	See product manual	Р
9.1.8	The packaging of those particle filtering half masks passing the dolomite clogging test shall beadditionally marked with the letter "D".		N
9.2	Particle filtering half mask	will will	Р
711	Particle filtering half masks complying with this European Standard shall be clearly and durably marked with the following:		Р
9.2.1	The name, trademark or other means of identification of the manufacturer or supplier.	Youshi protective equipment (Hangzhou) Co., Ltd	Р
9.2.2	Type-identifying marking.		Р
9.2.3	The number and year of publication of this European Standard.	THIS THIS	Р
9.2.4	The symbols FFP1, FFP2 or FFP3 according to class.	FFP2 NR	Р
9.2.5	If appropriate the letter D (dolomite) in accordance with clogging performance. This letter shall follow the class designation (see 9.2.4).	THIC THIC	N
9.2.6	Sub-assemblies and components with considerable bearing on safety shall be marked so that they can be identified.	.,(N



TMC Testing Services(Shenzhen) Co., Ltd			Report No.: TMC200320111-5		
110.	In. In.	EN 149	4 p. 4 p.	1	
Clause	Requirement – Test		Result - Remark	Verdict	

Attachments: Test table

Table 7.9.2	Penetration	Penetration of test aerosol test				
Models	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	Sample 6
Sodium chloride test 95 l/min	5.6	5.7	5.5	5.6	5.7	5.6
Paraffin oil test 95 l/min	5.4	5.6	5.7	5.7	5.6	5.5

Table 8.5	Leakage test					
Models	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	
NaCl flow rate (L/min)	90	100	120	110	120	
NaCl aerosol (um)	0.3	0.3	0.3	0.3	0.3	
0.3Pumping flow rate (L/min)	30	30	30	30	30	
NaCl concentration before mask (Mg/m3)	2	2	2	C 2	2	
NaCl concentration after mask (Mg/m3)	0.05	0.06	0.07	0.08	0.06	

Note: Test ark volume is 2m³

Average Leakage ratio is 8%<11% Calculation formula as below:

$$P(\%) = \frac{C_2}{C_1} \times \left(\frac{t_{IN} + t_{EX}}{t_{IN}}\right) \times 100$$

Table 8.9.2	Exhalation re	Exhalation resistance test				
Models tem	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	
Inhalation gas velocity (L/min)	160	160	160	160	160	
Maximum resistance (mbar)	2.45	2.47	2.45	2.46	2.46	

Table 8.9.3	Inhalation resistance test				CP	
Models Item	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5	
Inhalation gas velocity (L/min)	30	30	30	30	30	
Maximum resistance (mbar)	0.42	0.44	0.44	0.45	0.43	
Conclusion: Maximum Inhalation	resistance < 0.	7 mbar	,		,	



Access to global market
Testing Services(Shenzhen) Co., Ltd Report No : TMC200320111-S

TWO TESTING CETVICES (CHETZHEIT) CO.; Eta		4777		T (Op.	OIL IVO TWOZOL	002011110
110	Lin. Lin.	EN 149	110	110	11/1/	1
Clause	Requirement – Test			Result - Remark		Verdict

Table 8.9.3.2	Inhalation resistance test				Р
Models	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5
Inhalation (L/min)	95	95	95	95	95
Maximum resistance (mbar)	2.12	2.14	2.16	2.15	2.14



Photo Documentation



Photo 1 Overview

- End of Test Report -